

Rohi Stoffe gmbh
Ms. Kornelia Martin
postfach 747
82532 GERETSRIED
Duitsland

Antwort	Eingang
Bestätigt	
21. AUG. 2018	
WV	Gesamt
Ablage	

Your notice of
31-07-2018

Your reference

Date
08-08-2018

Analysis Report 18.04475.01

Required tests :

California Technical Bulletin 117 (2013)

Identification number	Information given by the client	Date of receipt
T1818342	MICA 95%WV/5%PA 600 g/m ² - VA835803 (piece #)	31-07-2018


Mieke Demeyer

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be
VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB



Reference: T1818342 - MICA 95%WV/5%PA 600 g/m² - VA835803 (piece #)

Section 1 : cover fabric test

Date of ending the test 07-08-2018
Standard used ASTM E1353-08a (2013)
Product standard California Technical Bulletin 117 (2013)

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

Filling T 30130 (Recticel) - non-fire retardant foam
Cover Sheeting Material Composition 100 % cotton - laundered
weight (125 ± 28) g/m²

	1	2	3
Open flaming	no	no	no
Smoulders more than 45 min.	no	no	no
Vertical char length > 45 mm	no	no	no

Test criteria

- no open flaming
- smouldering ≤ 45 minutes
- vertical char ≤ 45 mm

Requirements

- all specimens meet the test criteria → PASS
- two or more specimens fail the test criteria → FAIL
- one specimen fails the test criteria → 3 additional tests → PASS
all specimens meet the test criteria

Conclusion Pass