

DATE SUBMITTED: 01-SEPTEMBER-2016
DATE ISSUED: 07-SEPTEMBER-2016
REPORT NO: 38523
COMPANY ORDER NUMBER: Not Stated

CUSTOMER CONTACT NAME: SUSANNE HOFMANN (email: susanne.hofmann@rohi.com)
TEL: +49 8171 9354-30
FAX: +49 8171 9354-99

COMPANY: ROHI STOFFE GMBH
SCHOENLINDERSTRASSE 1
82538 GERETSRIED
GERMANY

CUSTOMER SAMPLE DESCRIPTION

FIBRE COMPOSITION: 95% WV, 5% PA
SAMPLE QUALITY/BATCH: VA826951
SAMPLE COLOUR: Not Stated
SAMPLE DESCRIPTION: Flat Woven Fabric without Flame Retardant Treatment - SHAKE
SAMPLE END USE: Seat Cover Fabric
FABRIC CUSTOMER: Not Stated
FABRIC SUPPLIER: rohi Stoffe GmbH

SPECIFICATIONS:

The Furniture & Furnishing (Fire) (Safety) (Amendment) Regulations 1988, S.I. No 1324

TEST METHOD:

BS 5852 Part 1: 1979 – Methods of test for the ignitability by smokers, materials of upholstered composites for seating

CLEANSING:

The sample was tested after the appropriate conditioning requirements.

CONDITIONING PRIOR TO TESTING:

The sample was conditioned immediately before the test for @ least 72 h in indoor ambient conditions and then for @ least 16 h at 20 +/- 5 °C and 50 +/- 20 % r h

Authorised signatures:

Signed: v

Zeb Alam
Technical Manager

TEST CERTIFICATE

DATE SUBMITTED: 01-SEPTEMBER-2016
 DATE ISSUED: 07-SEPTEMBER-2016
 REPORT NO: 38523
 COMPANY ORDER NUMBER: Not Stated

UPHOLSTERY FILLING SOURCE 0&1:

GRADE: Non Fire - Retardant Foam
 APPROX DENSITY: 20 – 22 kg per m³
 APPROX HARDNESS RANGE: 130 N
 SIZE OF TEST RIG:
 BACK JUNCTION: 450+/-2 mm x 300+/-2 mm
 SEAT JUNCTION: 450+/-2 mm x 150+/-2 mm

PROCEDURE:

The sample was mounted over foam as described above using the test rig as specified in BS 5852: 1979 Part 1, Clause 6 Apparatus

TESTING ENCLOSURE AND ATMOSPHERE:

The sample was tested in an atmosphere with a temperature of 15 °C to 30°C and a relative humidity of 20% to 70%. The sample was tested in an enclosure with a volume greater than 20m³

REQUIREMENTS:

Ignition Source: 0 (Cigarette)
 Progressive Smouldering (detected within duration): 60 minutes after ignition of cigarette
 Flaming (detected within duration): 60 minutes after ignition of cigarette
 Ignition Source: 1 (Match)
 Flaming (maximum duration): 2 minutes after ignition of burner
 Progressive Smouldering: *In compliance with The DTI guide to the FFSR page 20*

DATE OF TEST: 07-September-2016

Fire test carried out by: Peter Chan

RESULTS: The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Observation of test:

Ignition Sources		Position	Duration of		Special Features of Burning	
			Flames (minutes)	Smouldering (minutes)	Charring	Melting
Test 1	Source 0	LHS	00.00	Failed to smoulder	Yes	No
Test 2	Source 0	RHS	00.00	Failed to smoulder	Yes	No
Test 1	Source 1	LHS	00.00	00.00	Yes	No
Test 2	Source 1	RHS	00.00	00.00	Yes	No
LHS=Left Hand Side M= Middle RHS= Right Hand Side						

COMMENTS & OBSERVATIONS:

The sample tested complies with the flammability requirements of BS 5852: 1979 Part 1 ignition source 0 (cigarette) & source 1 (match) in accordance with the modifications stated in Schedules 4 & 5 of the Statutory Instruments 1988 No. 1324 Consumer Protection The Furniture & Furnishings (Fire) (Safety) Regulations 1988 & Amendment No. 2358 1989

Schedule 4 (cigarette) Test: **PASS (P0)**

Schedule 5 (match) Test: **PASS (P1)**

Please note: this test results issued on this certificate refer only to the item tested and therefore doesn't relate to the lot or batch of the product / sample. This test certificate shall not be duplicated.

Page 2 of 2

Textile Innovation House, 1 Lyons Road, Trafford Park, Manchester, M17 1RN
 T: 01204 840086 F: 01204 840524 E: technical@ifs-labs.com